



JACQUARD

• **FABRIC:** Woven in colorful yarn and fantasy

COMPOSITION: 60% Cotton - 40% Polyester

WEIGHT: 240g/m² (±5%) (without coating)

 $270 \text{ g/m}^2 (\pm 5\%)$ (with coating)

· COATING

PROCESS: Air scrape – ECO coating

TYPE OF COATING: Acrylic-vinyl copolymer preregistered REACH rules

INCREASE OF WEIGHT: 25-30 g/m²

It could change depending on the structure of the fabric

FINISHED: Fluorocarbon repellent oil - water with preregistered substances

REACH standards

The characteristics of the solidity to the light of the article doesn't change in respect the same article without coating.

MAINTENANCE:

·Clean with a damp cloth and neutral soap after use

·Machine wash up to 30°C (Domestic washing and use the delicate program)

·Always iron on the back up to 150°C

(It's very important to recover the "anti-stain" properties of the article)

No tumble dryDo not bleachDo not dry clean













· OIL REPELLENCY TEST:

OIL REPELLENCY RATIO: 7 (scale 1 to 8)Standard UNE-EN ISO 14419:2010

• WATER REPELLENCY TEST:

WATER REPELLENCY RATIO: 10 (scale 0 to 10)Standard Method 3M Test II

· WATER PENETRATION RESISTENCE TEST:

WATER PENETRATION RESISTANCE: 25 cm³/water Standard UNE-EN 20811:1993

Apparatus: Hydrostatic Head Tester

•WATER REPELLENCY, SPRAY TESTER:

WATER REPELLENCY: 100/100AATCC Test Method 22-2005

· CHARACTERISTICS:

· HIGHT STAIN RESISTANCE

· EASY CLEAN









